



Natural
Rubber Latex



Lab & Utility

Conform[®]+

69-210 69-318
Natural Rubber Latex Glove

Handle the most intricate and delicate products with incredible sensitivity

FEATURES AND BENEFITS:

Comfort, Strength and Sensitivity

The strength and comfort of 100% natural rubber latex, 5 mil thickness for the highest degree of sensitivity

2 versions available to better fit your needs

69-210: Powdered, smooth Grip

69-318: Powder Free, textured finish
for better grip

Food compliant

Conform[®] gloves comply with FDA food handling requirements (21 CFR 177.2600).



Ansell

TECHNICAL DATA SHEET:

PRODUCT INFORMATION:

| | 69-210 | 69-318 |
|--------------------------|---|--|
| Material | Natural Rubber Latex | |
| Color | Natural | |
| Glove Design | Ambidextrous, Powdered, Smooth Grip | Ambidextrous, Powder Free, textured Grip |
| Cuff | Beaded Cuff | |
| Audit Standards | ISO 9001:2008, ISO 13485:2003, US FDA 21 CFR PART 820 (QSR), and Canadian MDR | |
| Quality Control | Incoming for both raw materials and packaging materials, in-process (QA pre-packing inspection) and final release (QA pre-shipment inspection) for all gloves produced. | |
| Packaging | 100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper cartons | |
| Storage | Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition. | |
| Country of Origin | Malaysia | |

PHYSICAL PROPERTIES:

| PROPERTY | SIZE | TYPICAL VALUES | | | | | TESTING METHOD |
|---|------------------------|------------------------|-----|--------------------|-----|---------------------|-------------------|
| | | XS | S | M | L | XL | |
| Length (mm) | 69-210 | NA | 240 | 240 | 240 | 240 | ASTM D3767/EN 420 |
| | 69-318 | 240 | 240 | 240 | 240 | 240 | |
| Average Palm Width (mm) | 69-210 | NA | 80 | 95 | 102 | 111 | ASTM D3767/EN 420 |
| | 69-318 | 75 | 85 | 95 | 106 | 116 | |
| Freedom from Holes (Inspection level I) | 1.5 AQL | | | | | ASTM D5151/EN 374-2 | |
| Palm Thickness Single Wall | 69-210 | 69-318 | | | | ASTM D3767/EN 420 | |
| | (mm: 0.10) / (mils: 4) | (mm: 0.12) / (mils: 5) | | | | | |
| | BEFORE AGING | | | AFTER AGING | | | |
| Ultimate Tensile Strength | Min 18 Mpa | | | Min 14 Mpa | | ASTM D 412-06a | |
| Allongement à la rupture (%) | Min 650 | | | Min 500 | | ASTM D 412-06a | |

ORDERING INFORMATION:

| | SIZE | XS | S | M | L | XL |
|--------|--------|--------|--------|--------|--------|--------|
| 69-210 | ASPEN | NA | 516704 | 516705 | 516706 | 516707 |
| | ORACLE | NA | 104986 | 104987 | 104988 | 104989 |
| 69-318 | ASPEN | 516699 | 516700 | 516701 | 516702 | 516703 |
| | ORACLE | NA | 105072 | 105073 | 105074 | 105075 |



For additional information visit us at www.ansell.com, or call us at
 North America, Latin America and Caribbean: +1800 800 0444
 Asia Pacific: +852 2185 0600
 Europe: +32 2 528 74 00
 Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.