

Iron Stone^{TM/MC} Acrylic Seal



Acrylic seal for resilient and stone surfaces with excellent leveling and adhesive characteristics, even on worn surfaces.

Effective

- Superior compatibility for a wide range of resilient and stone surfaces
- Protects against soil penetration and staining

Easy to Use

- Top coat using any Diversey finish
- Strips easily with any Diversey stripper

Designed For

- Education
- Government
- Retail
- BSC





Use Overview

Iron Stone^{TMMC} **Acrylic Seal** seals stone, resilient and porous surfaces with excellent leveling and adhesive characteristics, even on worn surfaces. It has superior compatibility with a wide range of stone surfaces.

- Do not dilute (when applicable).
- Do not use on surfaces colder than 50° F (10° C).
- To avoid contamination, do not return unused product to original container.

Note: Floors will be slippery when wet or contaminated with foreign materials. Promptly clean-up spills and foreign materials. Meets ASTM D-2047 requirement for slip resistance.

Preparation

- Blockade areas to be stripped, sealed or finished. Floors will be very slippery until dry.
- Before first application of Iron Stone^{TMMC} Acrylic Seal remove all old coatings with any Diversey stripper.

Product Specifications

| Description | |
|------------------|--------------------------|
| Color/Form | Opaque white liquid |
| Flash Point | > 200° F (> 93.4° C) |
| рН | 8.2 |
| Scent | Solvent ammonia |
| Shelf Life | 2 years |
| Slip Resistance | 0.5 minimum (ASTM D2047) |
| Solids % | 18 |
| Solubility | Dispersible |
| Specific Gravity | 1.024 |

Available items

| Product Code | Description/Package Size | Dilution |
|--------------|---|--------------|
| 4006110 | 4 x 1 gallon / 3.78 L Containers | Ready-To-Use |
| 5104837 | 1 x 5 gallon / 18.9 L Envirobox ^{™/MC} | Ready-To-Use |

Safety Reminder

Please make sure your employees read and understand the product label and Material Safety Data Sheet before using this product. The label contains directions for use, and both the label and MSDS contain hazard warnings, precautionary statements and first aid procedures. MSDS are available on-line at www.diversey.com or by calling 888 352 2249.

Hazard Rating

| HMIS | | NFPA |
|------|--------------|------|
| 1 | Health | 1 |
| 0 | Flammability | 0 |
| 0 | Reactivity | 0 |

4=Very High; 3=High; 2=Moderate; 1=Slight; 0=Insignificant.



Coating

- Apply 1–2 uniform coats of Iron Stone^{™MC} Acrylic Seal using a clean mop.
- Allow 30–45 minutes drying time between coats. Temperature, humidity and ventilation may affect drying time.

Top Coating

Use Diversey finish based on desired gloss and equipment.

