

<b>QUALITE :</b>	<b>TINTED COPY PAPERS</b>		
<b>Certificat Forestier</b>			
<b>Pulp</b>	<b>ECF</b>		
<b>pH</b>	<b>Neutral</b>		
<b>Grammage</b>	<b>80</b>	<b>g/m<sup>2</sup></b>	<b>NF EN ISO 536</b>
<b>Thickness</b>	<b>106</b>	<b>microns</b>	<b>NF EN ISO 534</b>
<b>Bulk</b>	<b>1,33</b>	<b>cm<sup>3</sup>/g</b>	<b>NF EN ISO 534</b>
<b>Roughness Bendtsen</b>	<b>150</b>	<b>ml/min</b>	<b>ISO 8791-2</b>
<b>Moisture content</b>	<b>4,60</b>	<b>%H<sub>2</sub>O</b>	<b>NF EN ISO 20287</b>
<b>Relative humidity</b>	<b>32</b>	<b>% H<sub>2</sub>O dans l'air</b>	<b>sabre</b>
<b>Permanence</b>	<b>ISO 9706</b>		<b>NF EN ISO 9706</b>